

SECTION 040513

MORTAR AND MASONRY GROUT

PART 1 GENERAL

1.01 REFERENCES

- A. Standards:
 - 1. Mortar: ASTM C 270, except as otherwise specified.
 - 2. Grout: ASTM C 476.

1.02 SUBMITTALS

- A. Product Data:
 - 1. Portland Cement: Brand and manufacturer's name.
 - 2. Masonry Cement: Brand and manufacturer's name.
 - 3. Lime: Brand and manufacturer's name.
 - 4. Sand(s): Location of pit, name of owner, and previous test data.
 - 5. Color Pigments: Brand and manufacturer's name.

1.03 DELIVERY, STORAGE, AND HANDLING

- A. Deliver, store, and handle materials in a manner which will insure the preservation of their quality and fitness for the Work.
- B. Store cement and lime on raised platforms under waterproof, well ventilated cover.

PART 2 PRODUCTS

2.01 MATERIALS

- A. Cement: One of the following complying with the indicated requirements:
 - 1. Portland Cement: ASTM C 150, Type 1, of natural color or white as required to produce the desired color.
 - a. Fly Ash: Comply with ASTM C593.
 - 1) Recycled Content: Minimum 15 percent pre-consumer recycled content at contractor's option.
 - a) Type 1: 81 g, 15 percent.
 - 2. Masonry Cement: ASTM C 91, of natural color or custom color as required to produce the desired color.
 - a. Fly Ash: Comply with ASTM C593.
 - 1.) Recycled Content: Minimum 5 percent post-consumer recycled content, or minimum 20 percent pre-consumer recycled content at contractor's option.
 - a) Type M: 27 g, 5 percent; 108 g 20 percent.
 - b) Type S: 26 g, 5 percent; 102 g, 20 percent.
 - c) Type N: 24 g, 5 percent; 96 g 20 percent.

- B. Hydrated Lime: ASTM C 207, Type S.
- C. Mortar Sand: ASTM C 144, except that for joints less than 1/4 inch thick use sand graded with 100 percent passing the No. 16 sieve.
 - 1. Sand for White Mortar: Natural white sand or ground white stone.
 - 2. Sand for Colored Mortar: Ground marble, granite, or other sound stone, as required to match approved sample.
- D. Grout Sand: ASTM C 404.
- E. Color Pigments: High purity, finely ground, chemically inert, unfading, lime proof mineral oxides specially prepared for use in mortar.
- F. Water: Clean and free of deleterious amounts of acids, alkalis, and organic materials.

2.02 MIXES

- A. Mortar for Unit Masonry: Comply with ASTM C 270, proportion specifications, except limit materials to those specified.
 - 1. Colored Mortar: Proportion color pigments with other ingredients as necessary to match required color, except limit pigments other than carbon black to a maximum of 10 percent of cement content by weight and limit carbon black to a maximum of 3 percent of cement content by weight.
- B. Grout: Comply with ASTM C 476. If grout types are not indicated on Drawings, furnish type (fine or coarse) most suitable for the particular job conditions to completely fill cavities and embed reinforcement and other built-in items.

PART 3 EXECUTION

3.01 INSTALLATION

- A. Refer to sections of Specifications which require mortar and masonry grout.

3.02 MORTAR SCHEDULE

- A. Where mortar types are not indicated on Drawings or specified, use types as follows:
 - 1. Type S for concrete masonry units.
 - 2. Type N for brick masonry units.
 - a. Proportion Portland cement, lime, and sand in a 1:1:6 ratio.

END OF SECTION